

# Bodyian Bodyian 2K Primer-Surfacer BP-5000

Version 24.03

---

## PRODUCT DESCRIPTION

---

### ■ Outline

Bodyian 2K primer-surfacer BP-5000 is a premium two-component acrylic urethane primer-surfacer designed for fast filling of repairs. BP-5000 sands easily without clogging the sandpaper and provides excellent adhesion, corrosion protection and gloss holdout.

BP-5000 offers excellent solvent resistance, gloss, DOI and color holdout when applied as directed. BP-5000 can be directly topcoated with any NOROO automotive topcoat.

### ■ Suitable Substrates

Treated steel

OEM finishes

Sanded body filler

Thoroughly dried two-component coats (urethane, epoxy, etc.)

### ■ Product Configuration

Product Name	Pack(ℓ)	Contents(ℓ)	Storage
Bodyian 2K Primer-Surfacer BP-5000	4.0	4.0	12 months
Bodyian Urethane Hardener PH-50	1.0	1.0	12 months
Bodyian Urethane Reducer MR-10, 20, 30	4ℓ , 16ℓ	4ℓ , 16ℓ	24 months

\* Standard temperature of storage is 20°C.

### ■ Mixing Viscosity

15~20 sec. Viscosity(A+B+T) Ford Cup #4 at 77°F (25°C)

### ■ Pot Life

4 hours at 77°F (25°C) after mixing

### ■ Reducer

	Temperature			
	5~15°C	10~25°C	20~30°C	30°C above
Partial	MR-10	MR-20	MR-30	MR-30
1~3 panels	MR-10	MR-20	MR-30	MR-30
4 panels or above	MR-10	MR-20	MR-30	MR-30

---

## APPLICATION GUIDE

---

## ■ Use

Stirring



Stir thoroughly before use.

Surface  
Preparation



Wipe dry with a clean cloth. Sand and eliminate all rust and corrosion.

Mixing  
Ratio



Product Name	Mixing Ratio
Bodyian 2K Primer-Surfacer BP-5000	4
Bodyian Urethane Hardener PH-50	1
Bodyian Urethane Reducer MR-10, 20, 30	0.5~1

\* Mix by volume.

Spray  
Condition



1~2.5 bar  
2~3 wet coats keeping 15~20cm from the surface



Fluid tip : 1.3~1.6mm, D.F.T.=40~60μm



Flash time : 5~10 min.  
Set time : 10 min.

Protective  
Equipment



Use fresh air mask or charcoal respirator to avoid inhaling or being exposed to fumes.

## ■ Drying Times

Time  
to sand



30mins / 60°C  
1.5hrs / 77°F (25°C)



Dry sand P400 - P600



Wet sand P600 - P800

In case of wet sanding, allow water to evaporate. Apply heat to ensure water has evaporated to prevent humidity blistering.

---

## ADDITIONAL INFORMATION

---

### ■ Time to Apply Topcoat

- 1) After applying PS-570, maximum hours to apply topcoat are 24 hours.
- 2) After 24 hours, sand with P600 and recoat.

### ■ Applicable Topcoats

Bodyian Basecoat / Clearcoat  
Bodyian Unitan  
Bodyian Excellent

## ■ VOC Content

VOC content of 4.3lbs/gal (530g/liter)

## ■ Notice

1. For 2K products, short pot life, delayed drying time or unreactive substance can occur depending on hardener volume. Thus please mix base(A) and hardener(B) according to the proper mixing ratio.
2. Stir thoroughly before use.
3. Avoid direct sunlight during delivery, storage and handling. Store in a cool, dry dark place under room temperature(5°C-35°C).
4. Keep container tightly closed and store upright. When spilled, absorb contents with sand.
5. During application(including touch-up application), color difference may occur depending on mixing ratio, painting tools and application method. It may occur in same color product and same LOT No.
6. Please check whether color difference occurred or not. If possible, apply the same LOT No. product in consistent application method.
7. Putty marks might appear when you directly apply over the lacquer coating. As time goes by, it can peel off.
8. Completely eliminate the moisture of spray equipment before use.  
Cleanse immediately after application not to have any leftover on spray equipment.
9. Suitable condition for application and hardening is 10°C or above.
10. Surface temperature must be at or above 3°C to avoid moisture condensation.
11. Do not mix with other paint products.
12. Proceed a test application before applying on a precedent or an old paint film (check adhesion, color spread and transparency).
13. Please refer to technical data sheet before system application(primer, midcoat and topcoat).
14. Please do not apply paint above 85% RH or below 5°C because it may influence physical properties.
15. Contents must not flow into drain, river and soil.
16. Hardener must be stored under room temperature, avoid direct sunlight and keep away from humidity.
17. To prevent environmental pollution, dispose contents after complete use and dispose the residue through waste disposal company authorized by the ministry of environment.
18. Beware of ingestion, inhalation and contact of animals and plants.
19. Use masking tape, covering tape, vinyl or newspapers to cover areas that should not be painted.

## ■ Health and Safety

1. Be well-informed of MSDS before use.
2. Keep out of the reach of infants and children. Do not apply a product to baby products and food containers.
3. Do not use a product for any other uses. (Sniffing is prohibited. Do not use as a fuel.)
4. If on skin or eye, wash thoroughly with running water and get a medical treatment.
5. Do not apply a product in an enclosed area.  
In order to prevent suffocation during application and drying, use power blower to keep the area fully ventilated. Workers must wear gas mask and safety gears all the time.
6. Contents include organic solvents and can cause health problems such as headache, dizziness and dermatitis.

**Do not ingest or inhale the product and avoid skin contact.**

**Wear safety glasses, coveralls and latex gloves when mixing and applying.**

**7. Keep away from fire and heat during application or storage because it is flammable and has risk of fire.**

**Beware of spark from impact, droppage and friction while handling.**

**8. Storing a product with combustible substances such as stained clothes or paper may cause fire by spontaneous ignition. Thus do not pile products with combustible substances.**

**Keep it in a non-flammable container filled with water, then put a lid on and dispose it.**

**9. Please contact our customer service or refer to GHS-MSDS and technical data on the website for further details.**

This data sheet is based on the test results and experiential bases of NOROO but might vary with the actual working environment and applying condition. This data is the intellectual property of NOROO Paint thus copying and distribution without permission are strictly prohibited. For more information, please contact the technical team or refer to our homepage. (<http://www.autorefinishes.co.kr>)